DATASHEET

ASTM Property



LOTTE CHEMICAL

Grade	SFC-760D
Product	Polypropylene, Random Terpolymer

General Information

Key Features	- Medical application (Blow) - Excellent Clarity - USP Class VI, FDA DMF
Applications	- Medical port/cap

Item	Measuring Method	Unit	Value
Physical Properties			
Melt Flow Index (230℃, 2.16kg)	ASTM D1238	g/10min	16.0
Density	ASTM D792	g/㎤	0.9
Mechanical Properties			
Tensile Stress (Yield)	ASTM D638	kgf/㎠	220
Tensile Strain (Break)	ASTM D638	%	≥500
Flexural Modulus	ASTM D790	kgf/㎠	7500
Impact Properties			
Izod Impact Strength (notched, 23℃)	ASTM D256	kgf·㎝/㎝	10.0
Thermal Properties			
Melting Temperature	LC Method	℃	130
Heat Deflection Temperature (4.6kgf/㎠)	ASTM D648	℃	70
Film Properties			
Haze	ASTM D1003	%	<1.5
Coefficient of Friction	ASTM D1894		<0.8
Heat Seal Temperature	LC Method	℃	120

1. Physical Properties : these are not to be construed as specifications
2. Measured on 30㎛ mono-layer CPP film made of LOTTE CHEMICAL's cast film grade
3. ISO 9001, 14001, /TS 16949

* The last update date : 2022/09/21

LIMICO